

MS Thesis Presentation

Department of Biomedical Engineering

By: Xinyu Wu
Time: Friday, December 4th, 2015, 2:30 -4:00 pm
Place: Multimedia Room, BI 2504 (ITC)
Title of thesis: Optimization and Characterization of Multifunctional Polymer-based Nanoparticles Containing DTPA-Gd Contrast Agent for MRI Enhancement

Committee members

Dr. Amber L Doiron
Dr. Sha Jin
Dr. Chuan-Jian Zhong

Summary

The lack of specific and accurate imaging is an urgent issue for the prevention, diagnosis, and treatment of diseases such as cancer and atherosclerosis. Magnetic resonance imaging (MRI) is a promising modality for disease imaging without ionizing radiation. Diethylenetriaminepentaacetic acid gadolinium (III) (DTPA-Gd) is a FDA-approved MR contrast agent used to improve the visibility of internal body structures. Conjugation of the DTPA-Gd onto macromolecular polymers leads to high relaxivity and prolonged retention in blood circulation. More importantly, polymers can be applied to improve spatial and temporal biodistribution of loaded contrast agents.

A “theranostic” contrast agent including a high payload of DTPA-Gd for cancer detection was synthesized on the basis of polytyrosine polymer. The polytyrosine-DTPA-Gd particles were formed with near-spherical morphology, smooth surfaces, Gd attachment efficiency of 34.75 +/-7.59%, Gd loading of 0.013 mg Gd per mg of particles, and an average size of 217.9 +/-12.8 nm. Future studies will focus on adding MicroRNA therapeutics and aptamer targeting on the surface of polytyrosine.

Adding environmental sensitivity to contrast agents an oxidative-stress sensitive MRI contrast agent for atherosclerosis was designed by using polyamidoamine generation 5 dendrimer (PAMAM G5). PAMAM G5 was partially PEGylated using methoxy-poly (ethylene glycol)-carboxymethyl (mPEG-CM), and the remaining amine groups were conjugated with DTPA-Gd. The acid groups of mPEG-CM were activated by using carbodiimide chemistry. The PEG chain was used to form interpolymer complexation (IPC), blocking the T1 contrast-causing ability of DTPA-Gd. The relaxivity of PEG-G5-DTPA-Gd ($r_1 = 16.57 \text{ mM}^{-1}\text{s}^{-1}$, $r_2 = 44.63 \text{ mM}^{-1}\text{s}^{-1}$) is much higher than that of Gd chloride alone ($r_1 = 16.57 \text{ mM}^{-1}\text{s}^{-1}$, $r_2 = 44.63 \text{ mM}^{-1}\text{s}^{-1}$), indicating PEG-G5-DTPA-Gd is suitable for MRI enhancement. Additionally, the relaxivity of IPC-Gd ($r_1 = 8.56 \text{ mM}^{-1}\text{s}^{-1}$, $r_2 = 23.15 \text{ mM}^{-1}\text{s}^{-1}$) is lower than PEG-G5-DTPA-Gd, suggesting that interpolymer complexation is able to block the relaxivity of contrast agents. Future work will focus on the signal recovery under oxidative stress as well as *in vitro* studies.